

PRODUCT DESCRIPTION

CAFCO SprayFilm Topseal is a water-based two-part high performance epoxy sealer engineered as a sealer/top coat for CAFCO SprayFilm WB 4 Intumescent Coating System.

PRODUCT ADVANTAGES

- Provides excellent protection against weathering
- Water based epoxy system with low VOC's
- High solids content contributes to fast drying
- Low odor
- Easy application
- Cleans up with water

RECOMMENDED FINISH COATS

The following products are approved for application over CAFCO SprayFilm Topseal*

- Sherwin Williams Steel Master 9500
 - Sherwin Williams Acrolon 218HS
 - Tnemec Endura-Shield Series 73
 - Tnemec Enduralume Series 1077
 - Tnemec Endura-Shield II Series 1075
- * or other similar topcoats approved by Isolatek International.

FIRE TEST PERFORMANCE

CAFCO SprayFilm Topseal has also been tested for surface burning characteristics in accordance with ASTM E84 and is rated Class A.
 Flame Spread.....0-15 Smoke Developed.....0

APPLICATION

TEMPERATURE CONDITIONS:

Application Temperature: Apply SprayFilm Topseal when the ambient air temperature is between 50° - 100°F (10° - 38°C). A minimum substrate and ambient temperature of 50°F (10°C) shall be maintained prior to, during and a minimum of 24 hours after application.

APPLICATION EQUIPMENT:

Spray: Graco 1595 or equivalent, capable of maintaining 3000 psi (207 bar) 1.25 GPM (4.7 LPM) with a 60 mesh filter in pump. Recommend 50' of 3/8" (15 m of 10 mm) I.D. hose and a maximum of 6' (1.8 m) of 1/4" (6 mm) I.D. whip hose. Recommend Graco HD Texture Plus Spray Gun Model #241-705 or equivalent with the diffuser tip removed. Recommended tip size is 0.019" (0.48 mm) with the diffuser removed.

Brush: Use a soft/medium synthetic bristle brush.

Roller: Use 3/16" smooth finish nap roller.

SURFACE PREPARATION:

CAFCO SprayFilm WB 4: Surface must be clean and dry to ensure proper adhesion. A minimum of 5 days should be allowed for SprayFilm WB 4 to dry prior to applying SprayFilm Topseal. Alternatively, achieving a minimum Shore D value of 50 is recommended prior to applying SprayFilm Topseal. Increased drying time may be required under conditions of low air flow and/or high humidity.

(Continued on back page)

Technical Data

Color	Off-White
Finish	Gloss
Mixed Density	12.2 lbs per U.S. gal (1.46 g/cc)
Mix Ratio (A:B)	1:2 by volume, 1:2.8 by weight
Wet Film Thickness (WFT)	Total of 20 mils (0.52 mm), minimum, applied in two or more coats
Dry Film Thickness (DFT)	Total of 14 mils (0.36 mm), minimum, applied in two or more coats
Volume Solids v/v%	70 ± 2%
Theoretical Coverage	120 ft ² per 1.5 U.S. gal kit at 14 mils DFT (11.1 m ² per 5.68 L kit at 0.36 mm DFT)
VOC Value (combined)	0.20 lbs./gal (EPA method 24)
Dry Temperature Resistance	Continuous 175°F (79°C) Non-Continuous 200°F (93°C)

Packaging/Storage

Packaging	Two part individual pre-measured containers (Part A and Part B)
Net Contents	Kit: 1.5 U.S. gal / 17.25 lbs (5.68 L / 7.8 kg)
	Part A: 0.5 U.S. gal / 4.5 lbs (1.9 L / 2.04 kg)
	Part B: 1.00 U.S. gal / 12.75 lbs (3.78 L / 5.78 kg)
Gross Weight (Approx.)	20.0 lbs (9.1 kg)
Shelf Life	12 months in unopened sealed containers, properly stored.
Storage	Storage Temperature 40° - 100° F (4° - 38° C) Must protect from freezing and excessive heat. Store in a dry environment.

MIXING & THINNING:

Mixing: SprayFilm Topseal is supplied in 2 component pre-measured kits 1.5 U.S. gal (5.68 L). Pre-mix Part A and Part B with the paint stick provided to ensure any settled material is completely dispersed.

If crystallization is present in the Topseal Part A component, heat Part A contents to 100°F (38°C) for a minimum of 30 minutes or until crystallization is no longer present. Crystallization is a partial solidification of the liquid with a gritty feel and appearance.

Add all of Part A (clear) into Part B (off-white). Mix thoroughly with a paint style drill mixer for 3 minutes. Immediately add 12 oz (355 cc) of water and continue to mix for an additional 2 minutes.

Note: Continue to mix until a uniform white color is consistent throughout the mixture.

Ratio: 1:2 Ratio by volume (i.e. Part A to B) as supplied
Thinning: 12 ounces of water per 1.5 U.S. gal (5.68 L) kit
Pot Life: 60 minutes

CLEAN UP:

Clean up for all equipment and supplies must be done within a maximum of 10 minutes after the pot life has expired. Materials will cure or set-up in all equipment after that. Recommend adding 8 oz (225 g) of a "citrus" type or "alkaline" type industrial cleaner to a 5 U.S. gal (19 L) pail of clean water. Thoroughly flush all equipment and supplies with a minimum of two 5 U.S. gal (19 L) pails of the cleaning solution followed by minimum of two 5 U.S. gal (19 L) pails of potable water.

CURING SCHEDULE:

A minimum of 5 days should be allowed for SprayFilm WB 4 to dry prior to applying SprayFilm Topseal. A minimum of 24-hours and maximum of 14 days between coats of SprayFilm Topseal is required. SprayFilm Topseal must be finish coated within 14 days with an approved exterior finish coat.

LIMITATIONS:

Epoxies lose gloss and will discolor and chalk when exposed to sunlight.

CAFCO SprayFilm Topseal must be finish coated within 14 days. The SprayFilm Topseal/Finish Coat must be maintained throughout the life of the building to preserve the fire resistive rating of the CAFCO SprayFilm WB 4 Intumescent Coating.

HEALTH & SAFETY:

PRECAUTIONARY STATEMENT

Contains epoxy resin and polyamine curing agent. Avoid overexposure. Ensure ventilation is adequate. Four complete air exchanges per hour until material is dry. Avoid ingestion and contact with skin, eyes and clothing. Eye protection must be worn. Wash hands after using. Keep container closed when not in use. Do not transfer contents to the other containers for storage. **DO NOT TAKE INTERNALLY.**

EMERGENCY AND FIRST AID PROCEDURES

Skin Contact: During use, this product may cause local skin irritation. Avoid contact with skin. Wear rubber or latex type gloves. Wear typical long sleeve work clothing or a "Tyvek" type suit. Wash affected area immediately with soap and water for at least 15 minutes. Remove contaminated clothing. If irritation persists, seek medical attention.

Eye Contact: Wear proper eye protection; at minimum, safety glasses with side shields. Flush eyes with clean water for at least 15 minutes. If irritation persists, seek medical attention.

Inhalation: For confined areas or areas with poor ventilation, use an organic vapors cartridge type respirator. If adverse effects occur, remove to fresh air. If irritation persists, seek medical attention.

Ingestion: If swallowed drink one or two glasses of water to dilute. Do NOT induce vomiting. Consult a physician or Poison Control Center at once.

WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects and other reproductive harm.

Refer to Safety Data Sheet for complete information.

Contact Isolatek International's Technical Service Department at (800) 631-9600 for further top coat information.



ISOLATEK INTERNATIONAL is registered with the
AIA Continuing Education System (AIA/CES)



We support our customers with unsurpassed technical expertise and customer service, complemented by an extensive global network of experienced sales representatives and recognized applicators. For detailed product information or for the name of the sales representative in your area please contact us.

The performance data herein reflect our expectations based on tests conducted in accordance with recognized standard methods under controlled conditions. The applicator, general contractor, property owner and/or user MUST read, understand and follow the directions, specifications and/or recommendations set forth in Isolatek International's publications concerning use and application of these products, and should not rely merely on the information contained in this Technical Data Sheet. Isolatek International is not responsible for property damage, bodily injuries, consequential damages, or losses of any kind that arise from or are related to the applicator's general contractor's, or property owner's failure to follow the recommendations set forth in Isolatek International's publications. The sale of these products shall be subject to the Terms and Conditions set forth in the Company's invoices.



Isolatek International provides passive fireproofing materials under the CAFCO® and FENDOLITE® trademarks throughout the Americas and under the ISOLATEK® trademark throughout the remainder of the world.

800.631.9600 or 973.347.1200
www.isolatek.com | technical@isolatek.com

