

**X768**

**Structural Steel Rectangular Tube Columns  
Fendolite M-II and TG**

ASTM Desig.	Wall Thk	A/P	Metric Desig.	M/D	Hp/A	1-Hour	1-1/2 Hour	2-Hour	3-Hour	4-Hour
36 x 24	1/2	0.49	914 x 610 x 12.7	97.4	80.0	1/2	11/16	7/8	1-5/16	1-11/16
30 x 24	1/2	0.49	762 x 610 x 12.7	97.4	80.0	1/2	11/16	7/8	1-5/16	1-11/16
	3/8	0.37	x 9.5	73.8	105.5	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.31	x 7.9	61.4	126.8	11/16	1	1-5/16	1-15/16	2-5/16
28 x 24	1/2	0.49	711 x 610 x 12.7	97.4	80.0	1/2	11/16	7/8	1-5/16	1-11/16
	3/8	0.37	x 9.5	73.8	105.5	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.31	x 7.9	61.4	126.8	11/16	1	1-5/16	1-15/16	2-5/16
26 x 24	1/2	0.49	660 x 610 x 12.7	97.4	80.0	1/2	11/16	7/8	1-5/16	1-11/16
	3/8	0.37	x 9.5	73.2	106.4	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.31	x 7.9	61.4	126.8	11/16	1	1-5/16	1-15/16	2-5/16
24 x 22	1/2	0.49	610 x 559 x 12.7	96.8	80.5	1/2	11/16	7/8	1-5/16	1-11/16
	3/8	0.37	x 9.5	73.2	106.4	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.31	x 7.9	61.4	126.8	11/16	1	1-5/16	1-15/16	2-5/16
22 x 20	1/2	0.49	559 x 508 x 12.7	96.2	81.0	1/2	11/16	7/8	1-5/16	1-11/16
	3/8	0.37	x 9.5	73.2	106.4	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.31	x 7.9	61.4	126.8	11/16	1	1-5/16	1-15/16	2-5/16
20 x 18	1/2	0.49	508 x 457 x 12.7	96.2	81.0	1/2	11/16	7/8	1-5/16	1-11/16
	3/8	0.37	x 9.5	72.6	107.3	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.31	x 7.9	60.8	128.1	11/16	1	1-5/16	1-15/16	2-5/16
20 x 12	1/2	0.48	457 x 305 x 12.7	95	82.0	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.37	x 9.5	72.6	107.3	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.31	x 7.9	60.8	128.1	11/16	1	1-5/16	1-15/16	2-5/16
20 x 8	1/2	0.48	508 x 203 x 12.7	94.4	82.5	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	72	108.2	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.31	x 7.9	60.2	129.4	11/16	1	1-5/16	1-15/16	2-5/16
20 x 4	1/2	0.48	508 x 102 x 12.7	93.2	83.6	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	71.4	109.1	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	60.2	129.4	11/16	1	1-5/16	1-15/16	2-5/16
18 x 12	1/2	0.48	457 x 305 x 12.7	95	82.0	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.37	x 9.5	72	108.2	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.31	x 7.9	60.8	128.1	11/16	1	1-5/16	1-15/16	2-5/16
18 x 6	1/2	0.48	457 x 152 x 12.7	93.2	83.6	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	71.4	109.1	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	60.2	129.4	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	48.4	160.9	15/16	1-1/4	1-9/16	2-1/8	2-11/16
16 x 12	1/2	0.48	406 x 305 x 12.7	94.4	82.5	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	72	108.2	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.31	x 7.9	60.2	129.4	11/16	1	1-5/16	1-15/16	2-5/16
16 x 8	1/2	0.48	406 x 203 x 12.7	93.2	83.6	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	71.4	109.1	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	60.2	129.4	11/16	1	1-5/16	1-15/16	2-5/16

Note: A/P Ratio based on Design Formula

**X768**

**Structural Steel Rectangular Tube Columns  
Fendolite M-II and TG**

ASTM Desig.	Wall Thk	A/P	Metric Desig.	M/D	Hp/A	1-Hour	1-1/2 Hour	2-Hour	3-Hour	4-Hour
16 x 4	1/2	0.48	406 x 102 x 12.7	92	84.7	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.35	x 9.5	67.1	116.1	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	59.6	130.7	11/16	1	1-5/16	1-15/16	2-5/16
14 x 10	5/8	0.59	356 x 254 x 15.9	112.1	69.5	1/2	5/8	13/16	1-1/4	1-11/16
	1/2	0.48	x 12.7	93.2	83.6	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	71.4	109.1	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	60.2	129.4	11/16	1	1-5/16	1-15/16	2-5/16
14 x 6	1/2	0.48	356 x 152 x 12.7	92	84.7	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	70.8	110.0	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	59.6	130.7	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	48.4	160.9	15/16	1-1/4	1-9/16	2-1/8	2-11/16
14 x 4	1/2	0.47	356 x 102 x 12.7	91.5	85.1	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	70.2	110.9	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	59	132.0	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	47.8	162.9	15/16	1-1/4	1-9/16	2-1/8	2-11/16
12 x 8	5/8	0.59	305 x 203 x 15.9	112.7	69.1	1/2	5/8	13/16	1-1/4	1-11/16
	1/2	0.48	x 12.7	92	84.7	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	71	109.7	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	59.6	130.7	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	48.4	160.9	15/16	1-1/4	1-9/16	2-1/8	2-11/16
	3/16	0.18	x 4.8	36.6	212.8	15/16	1-1/4	1-9/16	2-1/8	2-11/16
12 x 6	5/8	0.58	305 x 152 x 15.9	111	70.2	1/2	5/8	13/16	1-1/4	1-11/16
	1/2	0.47	x 12.7	91.5	85.1	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	70.2	110.9	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	59	132.0	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	48.8	159.6	15/16	1-1/4	1-9/16	2-1/8	2-11/16
	3/16	0.18	x 4.8	36.6	212.8	15/16	1-1/4	1-9/16	2-1/8	2-11/16
12 x 4	5/8	0.58	305 x 102 x 15.9	109.2	71.3	1/2	5/8	13/16	1-1/4	1-11/16
	1/2	0.47	x 12.7	90.3	86.2	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	69.6	111.9	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	59	132.0	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	47.8	162.9	15/16	1-1/4	1-9/16	2-1/8	2-11/16
	3/16	0.18	x 4.8	36	216.3	15/16	1-1/4	1-9/16	2-1/8	2-11/16
10 x 8	5/8	0.58	254 x 203 x 15.9	110.2	70.7	1/2	5/8	13/16	1-1/4	1-11/16
	1/2	0.47	x 12.7	91.5	85.1	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	70.2	110.9	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	59	132.0	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	47.8	162.9	15/16	1-1/4	1-9/16	2-1/8	2-11/16
	3/16	0.18	x 4.8	36	216.3	15/16	1-1/4	1-9/16	2-1/8	2-11/16
10 x 6	5/8	0.58	254 x 152 x 15.9	110.2	70.7	1/2	5/8	13/16	1-1/4	1-11/16
	1/2	0.47	x 12.7	90.3	86.2	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.36	x 9.5	69.6	111.9	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	59	132.0	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	47.8	162.9	15/16	1-1/4	1-9/16	2-1/8	2-11/16
	3/16	0.18	x 4.8	36	216.3	15/16	1-1/4	1-9/16	2-1/8	2-11/16

Note: A/P Ratio based on Design Formula

**X768**

**Structural Steel Rectangular Tube Columns  
Fendolite M-II and TG**

ASTM Desig.	Wall Thk	A/P	Metric Desig.	M/D	Hp/A	1-Hour	1-1/2 Hour	2-Hour	3-Hour	4-Hour
10 x 4	1/2	0.46	254 x 102 x 12.7	88.5	88.0	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.35	x 9.5	68.4	113.9	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	58.4	133.4	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	47.2	165.0	15/16	1-1/4	1-9/16	2-1/8	2-11/16
	3/16	0.18	x 4.8	36	216.3	15/16	1-1/4	1-9/16	2-1/8	2-11/16
8 x 6	1/2	0.46	203 x 152 x 12.7	88.5	88.0	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.35	x 9.5	68.4	113.9	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	57	136.6	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	47.2	165.0	15/16	1-1/4	1-9/16	2-1/8	2-11/16
	3/16	0.18	x 4.8	36	216.3	15/16	1-1/4	1-9/16	2-1/8	2-11/16
8 x 4	1/2	0.46	203 x 102 x 12.7	86.7	89.8	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.35	x 9.5	67.9	114.7	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	57.2	136.2	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	46.6	167.1	15/16	1-1/4	1-9/16	2-1/8	2-11/16
	3/16	0.18	x 4.8	36	216.3	15/16	1-1/4	1-9/16	2-1/8	2-11/16
7 x 5	1/2	0.46	178 x 127 x 12.7	86.7	89.8	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.35	x 9.5	67.9	114.7	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.30	x 7.9	57.2	136.2	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	46.6	167.1	15/16	1-1/4	1-9/16	2-1/8	2-11/16
	3/16	0.18	x 4.8	36	216.3	15/16	1-1/4	1-9/16	2-1/8	2-11/16
7 x 4	1/2	0.46	178 x 102 x 12.7	87.4	89.1	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.35	x 9.5	66.7	116.8	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.29	x 7.9	56.6	137.6	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	46.6	167.1	15/16	1-1/4	1-9/16	2-1/8	2-11/16
	3/16	0.18	x 4.8	35.4	220.0	15/16	1-1/4	1-9/16	2-1/8	2-11/16
6 x 4	1/2	0.45	152 x 102 x 12.7	83.8	92.9	1/2	3/4	1-1/16	1-9/16	2-1/8
	3/8	0.35	x 9.5	66.1	117.8	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.29	x 7.9	56.1	138.8	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	46	169.3	15/16	1-1/4	1-9/16	2-1/8	2-11/16
	3/16	0.18	x 4.8	35.4	220.0	15/16	1-1/4	1-9/16	2-1/8	2-11/16
5 x 4	3/8	0.34	127 x 102 x 9.5	65	119.8	5/8	13/16	1-3/16	1-3/4	2-3/8
	5/16	0.29	x 7.9	55.5	140.3	11/16	1	1-5/16	1-15/16	2-5/16
	1/4	0.24	x 6.4	45.4	171.5	15/16	1-1/4	1-9/16	2-1/8	2-11/16
	3/16	0.18	x 4.8	34.8	223.8	15/16	1-1/4	1-9/16	2-1/8	2-11/16

Note: A/P Ratio based on Design Formula